



SPECIFICATION

(Reference sheet)

- Supplier : Samsung electro-mechanics - Samsung P/N : CL10C180JC8NNNC

Product : Multi-layer Ceramic Capacitor
 Description : CAP, 18pF, 100V, ± 5%, C0G, 0603

A. Samsung Part Number

<u>CL</u> <u>10</u> <u>C</u> <u>180</u> <u>J</u> <u>C</u> <u>8</u> <u>N</u> <u>N</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor				
2	Size	0603 (inch code)	L: 1.60 ± 0.10 mm	W: 0.80 ± 0.10 mm		
3	Dielectric	C0G	8 Inner electrode	Ni		
4	Capacitance	18 pF	Termination	Cu		
⑤	Capacitance	± 5%	Plating	Sn 100% (Pb Free)		
	tolerance		Product	Normal		
6	Rated Voltage	100 V	Special	Reserved for future use		
7	Thickness	0.80 ± 0.10 mm	① Packaging	Cardboard Type, 7" reel		

B. Structure and dimension



Samsung P/N	Dimension(mm)				
(Lead Free)	L	W	Т	BW	
CL10C180JC8NNNC	1.60 ± 0.10	0.80 ± 0.10	0.80 ± 0.10	0.30 ± 0.20	

C. Samsung Reliability Test and Judgement condition

Capacitance Within specified tolerance 1 Miz±10% / 0.5~5Vrms Q 760 min Insulation 10,000Mohm or 500Mohm×µF Rated Voltage 60~120 sec. Resistance Whichever is smaller Rated Voltage 60~120 sec. Appearance No abnormal exterior appearance Microscop (X10) Withstanding No dielectric breakdown or mechanical breakdown 200% of the rated voltage Voltage Temperature C0G Characteristics (From -55 °C to 125 °C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : with 1.0mm/sec. Bending to the limit (1mm) within ±5% or ±0.5pF whichever is larger SnAg3.0Cu0.5 solder Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder SnAg3.0Cu0.5 solder Question of the properties of the prope						
Rated Voltage 60~120 sec.						
Resistance Whichever is smaller Appearance No abnormal exterior appearance Microscop (X10) Withstanding No dielectric breakdown or mechanical breakdown 200% of the rated voltage Temperature C0G Characteristics (From -55 °C to 125 °C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : with 1.0mm/sec. Bending to the limit (1mm) within ±5% or ±0.5pF whichever is larger SinAg3.0Cu0.5 solder Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder						
Appearance No abnormal exterior appearance Microscop (X10) Withstanding No dielectric breakdown or mechanical breakdown 200% of the rated voltage Temperature C0G Characteristics (From -55 ℃ to 125 ℃, Capacitance change should be within ±30PPM/ ℃) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : within ±5% or ±0.5 pF whichever is larger Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5 ℃, 3±0.3sec.						
Withstanding No dielectric breakdown or voltage 200% of the rated voltage Voltage mechanical breakdown 200% of the rated voltage Temperature C0G Characteristics (From -55 °C to 125 °C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : with 1.0mm/sec. Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5 °C, 3±0.3sec.						
Voltage mechanical breakdown Temperature C0G Characteristics (From -55 °C to 125 °C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : with 1.0mm/sec. Bending to the limit (1mm) within ±5% or ±0.5 pF whichever is larger Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5 °C, 3±0.3sec.	Microscop (X10)					
Temperature COG Characteristics (From -55°C to 125°C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination Bending Strength Capacitance change: within ±5% or ±0.5pF whichever is larger More than 75% of terminal surface is to be soldered newly COG (From -55°C to 125°C, Capacitance change should be within ±30PPM/°C) Solg×F, for 10±1 sec. Bending to the limit (1mm) with 1.0mm/sec. SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec.						
Characteristics (From -55 °C to 125 °C, Capacitance change should be within ±30PPM/°C) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g×F, for 10±1 sec. Bending Strength Capacitance change : within ±5% or ±0.5pF whichever is larger Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5 °C, 3±0.3sec.						
Adhesive Strength of Termination Bending Strength Capacitance change: within ±5% or ±0.5pF whichever is larger More than 75% of terminal surface is to be soldered newly Solderability No peeling shall be occur on the 500g×F, for 10±1 sec. Bending to the limit (1mm) with 1.0mm/sec. SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec.						
of Termination terminal electrode Bending Strength Capacitance change : within ±5% or ±0.5pF whichever is larger Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec.	(From -55℃ to 125℃, Capacitance change should be within ±30PPM/℃)					
Bending Strength Capacitance change : within ±5% or ±0.5pF whichever is larger Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5℃, 3±0.3sec.						
within ±5% or ±0.5pF whichever is larger with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec.						
Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5 °C, 3±0.3sec.	Bending to the limit (1mm)					
is to be soldered newly 245±5 °C, 3±0.3sec.	with 1.0mm/sec.					
	SnAg3.0Cu0.5 solder					
(preheating : 80~120 ℃ for 10~30sec.)						
Resistance to Capacitance change : Solder pot : 270±5℃, 10±1sec.	Solder pot : 270±5℃, 10±1sec.					
Soldering heat within ±2.5% or ±0.25pF whichever is larger						
Tan δ, IR : initial spec.						
Vibration Test Capacitance change : Amplitude : 1.5mm	Amplitude : 1.5mm					
within ±2.5% or ±0.25pF whichever is larger From 10Hz to 55Hz (return : 1min.)						
Tan δ, IR : initial spec. 2hours ´ 3 direction (x, y, z)						
Moisture Capacitance change : With rated voltage	With rated voltage					
Resistance within ±7.5% or ±0.75pF whichever is larger 40±2°C, 90~95%RH, 500+12/-0hrs	40±2℃, 90~95%RH, 500+12/-0hrs					
Q: 160 min						
IR : 500Mohm or 25Mohm × μ F						
Whichever is smaller						
High Temperature Capacitance change : With 200% of the rated voltage						
Resistance within ±3% or ±0.3pF whichever is larger Max. operating temperature						
Q: 320 min 1000+48/-0hrs						
IR: 1,000Mohm or 50Mohm × μ F						
Whichever is smaller						
Temperature Capacitance change : 1 cycle condition						
Cycling within ±2.5% or ±0.25pF whichever is larger Min. operating temperature → 25°C	•					
Tan δ , IR : initial spec. \rightarrow Max. operating temperature \rightarrow 25 $^{\circ}$ C						
5 cycle test						

^{*} The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method:

Reflow (Reflow Peak Temperature: 260+0/-5°C, 10sec. Max)



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

- Disclaimer & Limitation of Use and Application -

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury.

We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- ① Aerospace/Aviation equipment
- ② Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- Military equipment
- 5 Disaster prevention/crime prevention equipment
- Any other applications with the same as or similar complexity or reliability to the applications set forth above.